



Typical Analysis

Cobalt	99.95%	Nickel	0.03%
Carbon	0.002%	Nitrogen	0.0001%
Copper	0.0005%	Oxygen	0.005%
Hydrogen	0.0005%	Silicon	0.0003%
Iron	0.001%	Sulphur	0.0002%
Lead	0.0002%	Zinc	0.0002%



Sizing

Bulk density of 25 mm squares:
Approx. 4.6 kg/dm³

Typical sizing: 25 mm X 25 mm (±5mm)

Guaranteed sizing: 94% with <30 mm X <30 mm

Standard Packaging



25 mm squares

4 x 250 kg steel drums, net weight 1,000 kg, strapped to a skidded wooden pallet.

Safety Data Sheet available upon request

Product Description

Nikkelverk COBALT has one of the lowest concentrations of total impurities of any commercially available COBALT.

Our COBALT is recommended for all high purity requirements, particularly superalloys, magnetic alloys, heat and wear resistant alloys, tool steels and other non-ferrous alloys.

The high purity of our COBALT makes it well suited for the production of catalysts, driers and other chemical uses.

Further information and assistance are available upon request and on the following webpages:

www.nikkelverk.no

www.glencore.com

**COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV GL**

= ISO 9001 =
= ISO 14001 =
= ISO 45001 =
= ISO 50001 =

The Quality Management System for the production of cobalt products at Nikkelverk's refinery located in Kristiansand, Norway is ISO 9001, ISO 14001, ISO 45001 and ISO 50001 registered.